



## Mars® 650: Ultra-High-Hardness Armor with maximum resistance to penetration

Mars® 650 is a ultra-high-hard (typical 650 HBW) protection steel offering uncompromising ballistic resistance performance, for use as add-on armor.

### PROPERTIES

#### STANDARDS

Mars® 650 can be ordered according to one of the following standards:

- > NF A36-800 THD5
- > MIL-DTL-32332

#### CHEMICAL COMPOSITION - LADLE ANALYSIS - MAX WEIGHT%

C	S	P	Si	Mn	Ni	Cr	Mo	B	CE 1)
0.55	0.002	0.010	1.0	0.7	2.4	0.4	0.5	0.003	0.83

1) Carbon equivalence per ASTM A6/A6M, i.e. :  $CE = C + [Mn/6] + [(Cr + Mo + V)/5] + [(Ni + Cu)/15]$

#### MECHANICAL PROPERTIES (IN BOTH DIRECTIONS)

	Hardness	Charpy KV 2) @-40°C standard 10 x 10 specimen 3)	
	HBW	J	ft.lbs
Guarantees	≥ 577	≥ 8	≥ 6
Typical values	650	9	7

2) Average of 3 tests. Single value min 70% of specified average.

3) For nominal thicknesses under 11mm, sub-size specimens are used. The specified minimum value is then proportional to the specimen cross section.

Brinell hardness test according to relevant standard (EN ISO 6506-1 / ASTM E10/E110), on each plate and in two places, one at each end of a diagonal, on a milled surface 0,5 to 1mm below plate surface.

Charpy Impact test according to relevant standard (EN ISO 148-1 / ASTM E23) on each heat and thickness from 6mm.

Ultrasonic test is performed according to standard requirements or upon special agreement up to EN 10160 Class S3/E4.

## IN SERVICE CONDITIONS

### BALLISTIC PROPERTIES

See our table of recommended minimum thicknesses for common protection levels.

Ballistic test to be performed upon request.

### PLATE PROCESSING

For all information concerning machining, cutting, or welding, see our userguide for Mars® protection steels.

## DELIVERY CONDITIONS

### HEAT TREATMENT

Mars® 650 is quenched and tempered at low temperature ( $\leq 180^{\circ}\text{C}$ ).

### SURFACE PROPERTIES

According to MIL-DTL-32332 or EN 10163 class B – subclass 3

Shot blasting and weldable primer application can be performed upon request

### SIZES AND TOLERANCES

Mars® 650 can be supplied as quarto plates or cut-to-length sheets (from hot strip mill) **in standard sizes or tailor made dimensions.**

	Quarto plates			Cut-to-length sheets
Thicknesses	4.0 – 16 mm (.157" – 0.787")			2.8 – 10.0 mm (.098" – .393")
Thickness Tolerances	Th	For width ≤2000mm	For width ≤2400mm	
	≥4 to ≤ 12 >12 to 20	0/+0.8 0/+1.0	0/+0.8 0/+1.2	≥2.5 to ≤ 8.5 : -0/+0.4 >8.5 to ≤ 10.0 : -0/+0.5
Width*	1000 – 2500 mm (39" – 98")			1000 – 2000 mm (39" – 78")
Length	1600 – 8100 mm (63" – 319")			1800 – 8100 mm (71" – 319")
Shape, length, and width tolerances as per MIL-DTL-32332 or EN 10029				

\* Depending on plate thickness

### FLATNESS

Maximum flatness deviation is 3mm/m (when measured according to EN 10029).

## YOUR CONTACT

**Leonard Peters**

**Tel. +27 10 222 0289**

[leonard@camsteel.co.za](mailto:leonard@camsteel.co.za)

<https://www.camsteel.co.za>

**CAM Steel South Africa**

1 Jockey Street  
Stormill  
Roodepoort  
Johannesburg

Technical data and information are to the best of our knowledge at the time of printing. However, they may be subject to some slight variations due to our ongoing research programme on protection steels. Therefore, we suggest that information be verified at time of enquiry or order. Furthermore, in service, real conditions are specific for each application. The data presented here are only for the purpose of description, and considered as guarantees when written formal approval has been delivered by our company. Further information may be obtained from the address opposite.